

# STAR PRIME™ Resins



Grade: PBTGF30  
Molding Grade 30% Glass Filled PBT

starplastics.com

## Typical Material Properties

326 Jack Burlingame Dr, Millwood, WV 25262 USA  
Phone: 304.273.0352, Fax: 304.273.0355

Physical	Nominal Values	ASTM Test
Specific Gravity	1.52	D792
<b>Mechanical</b>		
Tensile Strength at Break	18,500 psi	D638
Flexural Modulus	1,200,000 psi	D790
Flexural Strength at Yield	27,500 psi	D790
<b>Impact</b>		
Notched Izod Impact (73 °F, 0.125 in)	1.30 ft-lb/in	D256
<b>Thermal</b>		
DTUL @ 264 psi-unannealed (0.250 in)	385 °F	D648
<b>Mold Shrinkage</b>		
Linear Flow	.004 - .006 in/in	D955

The information provided above is based upon typical values, and are intended only as guides. Star Plastics, Inc./SDR Inc. assumes no obligation or liability for any advice furnished or for any results obtained with respect to this information. **No guarantees or warranties are expressed or implied.**

\*STARPRIME™ is a registered trademark of Star Plastics Inc; SDR Plastics Inc, its subsidiaries or affiliates.

## Recommended Processing Guidelines

	Nominal Values
Drying Time and Temperature	4.0 hr, 230 – 250 °F
Suggested Max Moisture	0.020%
Rear Temperature	450 – 480 °F
Middle Temperature	475 – 500 °F
Front Temperature	475 – 510 °F
Nozzle Temperature	475 – 510 °F
Processing (melt) Temperature	485 – 525 °F
Mold Temperature	150 – 210 °F
Back Pressure	50 – 100 psi
Screw Speed	40 – 75 rpm

The conditions listed above are only guidelines. You may want to adjust conditions to meet your requirements.

**Your Competitive Advantage in an Ever Changing Market!**