

VALUPAK™ Resins



Grade: PC2012R, PC2012FRR

Molding Grade PC, w/ Release, w/ Release and V2

326 Jack Burlingame Dr, Millwood, WV 25262 USA
Phone: 304.273.0352, Fax: 304.273.0355

Typical Material Properties

Physical	Nominal Values	ASTM Test
Specific Gravity	1.20	D792
Melt Flow (300 °C/1.2 kg)	20 g/10 min	D1238
Mechanical		
Tensile Modulus	340,000 psi	D638
Tensile Strength at Yield	8,300 psi	D638
Flexural Modulus	340,000 psi	D790
Flexural Strength at Yield	12,000 psi	D790
Impact		
Notched Izod Impact (73 °F, 0.125 in)	12 ft-lb/in	D256
Thermal		
DTUL @ 264 psi-unannealed (0.125 in)	260 °F	D648
Mold Shrinkage		
Linear Flow	.005 - .007 in/in	D955
UL Rating	V2 (1.5 mm)	UL 94

The information provided above is based upon typical values, and are intended only as guides. Star Plastics, Inc./SDR Inc. assumes no obligation or liability for any advice furnished or for any results obtained with respect to this information. **No guarantees or warranties are expressed or implied.**

*VALUPAK™ is a registered trademark of Star Inc; SDR Plastics Inc, its subsidiaries or affiliates.

Recommended Processing Guidelines

	Nominal Values
Drying Time and Temperature	4.0 hr at 250 °F
Suggested Max Moisture	0.020%
Rear Temperature	475 - 525 °F
Middle Temperature	500 - 550 °F
Front Temperature	525 - 575 °F
Nozzle Temperature	525 - 575 °F
Processing (melt) Temperature	525 - 575 °F
Mold Temperature	160 - 210°F
Back Pressure	50 - 200 psi
Screw Speed	40 - 100 rpm

The conditions listed above are only guidelines. You may want to adjust conditions to meet your requirements.

Your Competitive Advantage in an Ever Changing Market!