

# VALUPAK™ Resins



Grade: PC5FRGF10,PC5FRGF10R,PC5FRGF10UV,PC5FRGF10RUV  
Molding Grade PCFR w/10%Glass,Release,UV, Release and UV

326 Jack Burlingame Dr, Millwood, WV 25262 USA  
Phone: 304.273.0352, Fax: 304.273.0355

## Typical Material Properties

Physical	Nominal Values	ASTM Test
Specific Gravity	1.27	D792
Melt Flow (300 °C/1.2 kg)	5.0 g/10 min	D1238
<b>Mechanical</b>		
Tensile Modulus	450,000 psi	D638
Tensile Strength at Yield	9,500 psi	D638
Flexural Modulus	475,000 psi	D790
Flexural Strength at Yield	14,500 psi	D790
<b>Impact</b>		
Notched Izod Impact (73 °F, 0.125 in)	1.5 ft-lb/in	D256
<b>Thermal</b>		
DTUL @ 264 psi-unannealed (0.125 in)	270 °F	D648
<b>Mold Shrinkage</b>		
Linear Flow	.003 - .005 in/in	D955
<b>UL Rating</b>	VO (3.0 mm)	UL 94

The information provided above is based upon typical values, and are intended only as guides. Star Plastics, Inc./SDR Inc. assumes no obligation or liability for any advice furnished or for any results obtained with respect to this information. **No guarantees or warranties are expressed or implied.**

\*VALUPAK™ is a registered trademark of Star Plastics Inc; SDR Plastics Inc, its subsidiaries or affiliates.

## Recommended Processing Guidelines

	Nominal Values
Drying Time and Temperature	4.0 hr, 250 °F
Suggested Max Moisture	0.020%
Rear Temperature	550 - 600 °F
Middle Temperature	575 - 625 °F
Front Temperature	600 - 650 °F
Nozzle Temperature	600 - 650 °F
Processing (melt) Temperature	600 - 650 °F
Mold Temperature	50 - 200 °F
Back Pressure	40 - 100 psi
Screw Speed	25 to 75 rpm

The conditions listed above are only guidelines. You may want to adjust conditions to meet your requirements.

**Your Competitive Advantage in an Ever Changing Market!**