

# STAR Prime™ Resins



Grade: PC8053

Molding Grade PCFR with Release and UV

starplastics.com

## Typical Material Properties

326 Jack Burlingame Dr, Millwood, WV 25262 USA  
Phone: 304.273.0352, Fax: 304.273.0355

Physical	Nominal Values	ASTM Test
Specific Gravity	1.20	D792
Melt Flow (300 °C/1.2 kg)	25.0 g/10 min	D1238
<b>Mechanical</b>		
Tensile Modulus	350,000 psi	D638
Tensile Strength at Yield	9,000 psi	D638
Flexural Modulus	350,000 psi	D790
Flexural Strength at Yield	13,000 psi	D790
<b>Impact</b>		
Notched Izod Impact (73 °F, 0.125 in)	14.0 ft-lb/in	D256
<b>Thermal</b>		
DTUL @ 264 psi-unannealed (0.125 in)	260 °F	D648
<b>Mold Shrinkage</b>		
Linear Flow	.005 - .007 in/in	D955
<b>UL Rating</b>		
Flammability	V-0 @ 1.5mm	UL 94
RTI	80 °C, 80°C, 80 °C	UL746B

The information provided above is based upon typical values, and are intended only as guides. Star Plastics, Inc/SDR Inc assumes no obligation or liability for any advice furnished or for any results obtained with respect to this information. **No guarantees or warranties are expressed or implied.**

\*STARPRIME™ is a registered trademark of Star Plastics Inc; SDR Plastics Inc, its subsidiaries or affiliates.

## Recommended Processing Guidelines

	Nominal Values
Drying Time and Temperature	4.0 hrs at 250° F
Suggested Max Moisture	0.020%
Rear Temperature	520 - 550 °F
Middle Temperature	530 - 570 °F
Front Temperature	550 - 600 °F
Nozzle Temperature	550 - 600 °F
Processing (melt) Temperature	550 - 600 °F
Mold Temperature	170 - 220 °F
Back Pressure	50 - 100 psi
Screw Speed	40 - 75 rpm

The conditions listed above are only guidelines. You may want to adjust conditions to meet your requirements.

**Your Competitive Advantage in an Ever Changing Market!**