

Material Designation: PCQP7012

Product Description: Polycarbonate (PC), furnished as pellets

Color	Min. Thk (mm)	Flame Class	HWI	HAI	RTI Elec	RTI Imp	RTI Str
ALL	1.5	V-1	3	0	125	115	125
	3.0	V-0	2	1	125	115	125
	3.5	V-0	-	-	125	115	125

Comparative Tracking Index (CTI): 2
 Dielectric Strength (kV/mm): 24
 Dimensional Stability (%): 3
 High-Voltage Arc Tracking Rate (HVTR): 0

Inclined Plane Tracking (IPT): –
 Volume Resistivity (10^x ohm-cm): 15
 High Volt, Low Current Arc Resis (D495): 6

(f1) - Suitable for outdoor use with respect to exposure to Ultraviolet Light, Water Exposure and Immersion in accordance with UL 746C.

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliance, where the acceptability of the combination is determined by UL.

Report Date: 2002-06-11

Last Revised: 2009-11-19

2013 UL LLC©

**IEC and ISO Test Methods**

Test Name	Test Method	Units	Thickness	Value
			Tested (mm)	
Flammability	IEC 60695-11-10	Class (color)	1.5	V-1 (ALL)
			3.0	V-0 (ALL)
			3.5	V-0 (ALL)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	C	3.5	960
Glow-Wire Ignition (GWI)	IEC 60695-2-13	C	3.5	775
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	–	–
IEC Ball Pressure	IEC 60695-10-2	C	–	–
ISO Heat Deflection (1.80 MPa)	ISO 75-2	C	4.0	137
ISO Tensile Strength	ISO 527-2	MPa	–	–
ISO Flexural Strength	ISO 178	MPa	–	–
ISO Tensile Impact	ISO 8256	kJ/m ²	–	–
ISO Izod Impact	ISO 180	kJ/m ²	–	–
ISO Charpy Impact	ISO 179-2	kJ/m ²	–	–

Your Competitive Advantage in an Ever Changing Market!

Star Plastics, Inc

326 Jack Burlingame Dr, Millwood, WV 25262 USA

Phone: 304.273.0352, 304.273.5326

