

GRADE: PC8010

Molding Grade PCFR without Release or UV

Typical Material Properties

Physical	Nominal Values	ASTM Test
Specific Gravity	1.20	D792
Melt Flow (300°C/1.2kg)	8.0 g/10 min	D1238
Mechanical		
Tensile Modulus	350,000 psi	D638
Tensile Strength @ Yield	9,000 psi	D638
Flexural Modulus	350,000 psi	D790
Flexural Strength @ Yield	13,000 psi	D790
Impact		
Notched Izod Impact (73 °F, 0.125 in)	14.0 ft-lb/in	D256
Thermal		
DTUL @ 264 psi-unannealed (0.125 in)	260 °F	D648
Mold Shrinkage		
Linear Flow	.005 - .007 in/in	D955
UL Rating		
Flammability	V-0 @ 1.5mm	UL 94
RTI	80°C, 80°C, 80°C	UL746B

The information provided above is based upon typical values, and is intended only as a guide. Star Plastics, LLC assumes no obligation or liability for any advice furnished or for any results obtained with respect to this information. *No guarantees or warranties are expressed or implied.*

Orion[®] is a registered trademark of Star Plastics, LLC, its subsidiaries or affiliates.

Recommended Processing Guidelines

	Nominal Values
Drying Time and Temperature	4.0 hrs, 250°F
Suggested Max Moisture	0.020%
Rear Temperature	520°F – 550 °F
Middle Temperature	530°F – 570 °F
Front Temperature	550°F – 600 °F
Nozzle Temperature	550°F – 600 °F
Processing (Melt) Temperature	550°F – 600 °F
Mold Temperature	170°F – 220 °F
Back Pressure	50 – 100 psi
Screw Speed	40 – 75 RPM

The conditions listed above are only guidelines. You may want to adjust conditions to meet your requirements.