

GRADE: ORION® PCGFO, PCGF 10R, PCGF 10UV, PCGF 10RUV

Molding Grade PC with 10% Glass, with Release, with UV, with UV & Release

Typical Material Properties

Physical	Nominal Values	ASTM Test
Specific Gravity	1.27	D792
Melt Flow (300°C/1.2 kg)	15.0 g/10 min	D1238
Mechanical		
Tensile Modulus	450,000 psi	D638
Tensile Strength @ Yield	9,500 psi	D638
Flexural Modulus	450,000 psi	D790
Flexural Strength @ Yield	14,500 psi	D790
Impact		
Notched Izod Impact (73°F, 0.125 in)	1.0 ft-lb/in	D256
Thermal		
DTUL @ 264 psi – Unannealed (0.125 in)	275°F	D648
Mold Shrinkage		
Linear Flow	.003 – .005 in/in	D955

The information provided above is based upon typical values, and is intended only as a guide. Star Plastics, LLC assumes no obligation or liability for any advice furnished or for any results obtained with respect to this information. *No guarantees or warranties are expressed or implied.*

Orion® is a registered trademark of Star Plastics, LLC, its subsidiaries or affiliates.

Recommended Processing Guidelines

	Nominal Values
Drying Time and Temperature	4.0 hrs at 250°F
Suggested Max Moisture	0.020%
Rear Temperature	550 – 600°F
Middle Temperature	575 – 625°F
Front Temperature	600 – 650°F
Nozzle Temperature	600 – 650°F
Processing (Melt) Temperature	666 – 650°F
Mold Temperature	50 – 200°F
Back Pressure	40 – 100 psi
Screw Speed	25 – 75 RPM

The conditions listed above are only guidelines. You may want to adjust conditions to meet your requirements.