

Grade: re-PCR-FR2114(f1)

Molding Grade PCFR, with Elevated RTI's and (f1)

Including 50% Pre-consumer Validated Recycled Content Materials

Typical Material Properties

| Physical | Nominal Values | ASTM Test |
|--|----------------------------------|------------------|
| Specific Gravity | 1.20 | D792 |
| Melt Flow (300°C/1.2 kg) | 19.0 g/10 min | D1238 |
| Mechanical | | |
| Tensile Modulus | 345,000 psi | D638 |
| Tensile Strength @ Yield | 8,500 psi | D638 |
| Flexural Modulus | 345,000 psi | D790 |
| Flexural Strength @ Yield | 13,000 psi | D790 |
| Impact | | |
| Notched Izod Impact (73°F, 0.125 in) | 14.0 ft-lb/in | D256 |
| Thermal | | |
| DTUL @ 264 psi – Unannealed (0.125 in) | 260°F | D648 |
| Mold Shrinkage | | |
| Linear Flow | .005 – .007 in/in | D955 |
| UL Rating | | |
| Flammability | (f1) | UL746C |
| RTI | V-0 @ 3mm 125°C, 115°C, 125°C | UL 94 UL 746B |

The information provided above is based upon typical values, and is intended only as a guide. Star Plastics, LLC assumes no obligation or liability for any advice furnished or for any results obtained with respect to this information. *No guarantees or warranties are expressed or implied.*

reNova™ is a registered trademark of Star Plastics, LLC, its subsidiaries or affiliates.

Recommended Processing Guidelines

| | Nominal Values |
|-------------------------------|------------------|
| Drying Time and Temperature | 4.0 hrs at 250°F |
| Suggested Max Moisture | 0.020% |
| Rear Temperature | 520 – 550°F |
| Middle Temperature | 530 – 570°F |
| Front Temperature | 550 – 600°F |
| Nozzle Temperature | 550 – 600°F |
| Processing (Melt) Temperature | 550 – 600°F |
| Mold Temperature | 170 – 220°F |
| Back Pressure | 50 – 100 psi |
| Screw Speed | 40 – 75 RPM |

The conditions listed above are only guidelines. You may want to adjust conditions to meet your requirements.